

- High Thermal Conductivity
- Low Compression Stress
- High Reliability
- Automatic Dispensing
- Consumer Electronics
- Communication Equipment

could be used for automatic dispensing and screen printing.

	Silicone Filled with Thermal Powder &		—
	Blue-Green	—	Visual
	10.0	W/m·K	ASTM D5470
	28	g/min	30cc EFD, 90Psi
	3.2	g/cm^3	ASTM D792
	-40 - 150	°C	—
	6.5	KV/mm	ASTM D149
	V-0	—	UL 94
	YES	—	—
	6	month	25±5°C, ≤50% RH

All technical information stated in this technical data have been confirmed that all the technical parameters are reliable after harsh testing and evaluation of them.